



Product Description

Berger RustPro is a semi-industrial, anti-rust, gloss enamel paint, specially formulated with anti-corrosive properties, to resist the harsh tropical Caribbean weather. For exterior and interior use on metal and wood where a premium quality, fast drying coating with excellent gloss retention and durability are desired.

Design Use

• Areas of use: Interior/Exterior, metal and wood.

Application Data

Application:	Brush, Roller, Spray.
Spreading Rate:	At 25 microns, approx.11 sq. metres per litre, 42 m ² (400 sq ft) per gallon (3.8 litres) depending on the porosity and texture of the surface.
Drying Time:	Touch dry 1-2 hours at ambient temperature. Hard dry- Approximately 3.5 hours dust free at 25° C Recoat 6 hours.
Pack Sizes:	3.8 litre, 950 ml
Dry Film Thickness:	25 – 40 Microns per coat.
Colour Range:	7 Standard colours including black and white
Thinning/clean Up:	Berger No. 2 Reducer.
Solvent Resistance:	Resistance to aliphatic hydrocarbons and alcohol. Polar solvents & chlorinated solvents are liable to attack the film.

Additional Information

Temperature Limitation:	Up to 120°F
Flash Point:	36.7° C, 98°F.
Pot Life:	Not applicable.
Finish:	High Gloss.

Surface Preparation

Previously Painted Metal

Surface must be clean and free from dirt and grease. Remove rust and scale from exposed metal by wire-brushing etc. Apply one coat of Berger RustPro Primer or Berger Red Oxide Primer to exposed areas. Once completely dry (overnight) apply 1 to 2 top coats of Berger RustPro Enamel over the entire surface.

New Metal

New metal must be clean and clear of any rust, grease, dirt or scale. Apply 1 coat of Berger RustPro Primer or Berger Red Oxide Primer. Finish with 1 to 2 topcoats of Berger RustPro Enamel.

Aluminium/Galvanized Metal

Clean surface with Berger No.2 Reducer to remove any grease. Treat the surface with Berger Self Etch Primer. Apply Berger RustPro Primer followed by 1 to 2 coats of Berger RustPro Enamel.

Previously Painted Wood

Should be clean, dry and free from dirt. Sand where necessary. Apply 1 to 2 topcoats of Berger RustPro Enamel.

New Wood

Surface should be clean, dry and free from dirt. Seal all knots with Berger Knotting Varnish. The first coat on bare wood should be thinned by not more than 10% per 3.8 litres, with Berger #2 Reducer. For best results, apply one coat of Berger Wood Primer or Berger Undercoat, and apply 1 to 2 coats of Berger RustPro Enamel to a completely dry surface.

Application

Ensure adequate ventilation during application and drying. Do not apply when humidity exceeds 95% and condensation is likely. Only apply coating when surface temperature is 3°C or more above dew point.

Use 5% to 10% of Berger #2 Reducer for ease of application if necessary. Do not over dilute.

Roller: Recommended. Apply an even coat taking care to avoid runs and sags. Minimum two coats recommended.

BERGER
RustPro Premium Anti-Rust Gloss Enamel

Health & Safety

Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust mask and gloves. Use a barrier cream.

Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour.

First Aid

Eyes: In the event of accidental splashes, flush eyes with warm water immediately and obtain medical advice.

Skin: Wash skin thoroughly with soap and water or approved industrial cleaner. **DO NOT USE** solvent or thinners.

Inhalation: Remove to fresh air, loosen collar and keep patient rested.

Ingestion: In case of accidental ingestion **DO NOT INDUCE VOMITING**. Obtain immediate medical attention.

Recommended paint solutions Step 1

**For priming metal
close to or by the sea**



Apply 1 coat
**BERGER RustPro
Metal Primer**

**For priming wood
close to or by the sea**



Apply 1 coat
**BERGER Wood Primer
for new wood.**

Contact Berger Technical for more information on surface preparation.

Step 2



Apply 1 to 2 coats **BERGER RustPro
Premium Anti-Rust Gloss Enamel**
to properly prepared Metal or wood.

Contact Us



Berger Paints Jamaica Ltd.
256 Spanish Town Road,
P.O. Box 8, Kingston 11, Jamaica
Tel: +1-876-923-6226
Fax: +1-876-923-5129
Email: bergerja_marketing@bergeronline.com

www.bergercaribbean.com

[facebook.com/BergerCaribbean](https://www.facebook.com/BergerCaribbean)

These suggestions and data are based on information we believe to be reliable. They are offered in good faith but without guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale. Suggestions for uses of our products should not be understood as recommendations that they be used in violation of any patent or regulations. For specific recommendations, contact your Berger Technical Service Representative or Technical Service Department.

