



## Product Description

**Berger Marine Enamel** is a premium, high gloss enamel that provides superior durability and weathering performance in a marine or light industrial environment. It exhibits a high resistance to moisture and sunlight and its superior high gloss combined with anti-corrosive properties, make **Berger Marine Enamel** a great topcoat for use on superstructure, deck work including masts, funnels for accommodation space and inboard work. **Berger Marine Enamel** is easy to apply by brush, roller or spray and has excellent coverage.

## Design Use

**AREAS OF USE:** Exterior

## Technical Data

**FINISH:** Gloss  
**COLOUR:** N/A  
**THINNER/CLEANER:** Berger Reducer No. 2.  
**COVERAGE:** 10 sq. metres per litre.  
**DRYING TIME:** Touch Dry - 2 to 4 hours. Hard Dry - 16 hours.  
Overcoat 16 hours minimum. 10 days maximum

## Application Method

Brush, Roller, Conventional and Airless Spray.

## Surface Preparation

### IRON AND STEEL:

Hand or power tool clean to remove all rust, millscale, grease, oil or dirt.

### ALUMINIUM AND ZINC:

Remove all grease and oil with Industrial Detergent or Berger Reducer No. 2 and treat with Berger Self Etch Primer.

### WOOD:

Make sure wood is thoroughly dry and clean.

### FIBRE GLASS:

Clean to remove release agents, dirt and grease. Rub down with 240 grade water-proof abrasive paper.

## PRIMING

### IRON AND STEEL:

Berger Zinc Chromate Primer, Berger Universal Metal Primer, or Berger Navy Protective.

### FIBRE GLASS:

No primer required.

### WOOD:

Apply two (2) coats Berger Knotting Varnish to all knots and resin pockets then apply two (2) coats Berger Wood Primer White thinning, the first coat 25% with Berger Reducer No. 2. If necessary, fill nail holes, joints, etc. between coats.



# BERGER Marine Enamel

## Safety Precautions

### READ DIRECTIONS CAREFULLY BEFORE USE

Do not take internally.

Liquid paint and vapours may cause irritation.

Use only with adequate ventilation.

To ensure the entry of fresh air, open all windows and doors. If headache or dizziness is experienced, use respiratory protection or leave area for fresh air. Avoid contact with skin or eyes.

## First Aid

**INGESTION:** Do not induce vomiting. Get medical attention immediately.

**INHALATION:** If excessive exposure symptoms are experienced, leave area to obtain fresh air. If difficulty continues, seek immediate medical attention.

**EYE CONTACT:** Flush immediately with water for at least 15 minutes

**SKIN CONTACT:** Wash thoroughly with soap and water

## Recommended Paint Solutions Step 1

For priming new  
wood surface



Apply 1 coat of  
Berger Wood Primer

For priming new  
metal surface



Apply 1 coat of  
Berger Zinc Chromate  
Metal Primer

## Step 2



Apply 1 to 2 coats of  
Berger Marine Enamel

## Contact Us



**Berger Paints Barbados Ltd.**  
Exmouth Gap, Brandons, St. Michael,  
Bridgetown, Barbados, W.I. BB12069  
Tel: +1-246-425-9073  
Fax: +1-246-228-0866  
Email: info@bergeronline.com

[www.bergercaribbean.com](http://www.bergercaribbean.com)

[facebook.com/BergerCaribbean](https://www.facebook.com/BergerCaribbean)

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.

